


YAC-A210

3-Aminopropyl(diethoxy)methylsilane

CAS No. 3179-76-8



Specifications:

| Items | Specification |
|------------------|---------------------------------|
| Appearance | Colorless transparent liquid |
| Assay | ≥98.0% |
| Color | ≤30 |
| Density | 0.9110~0.9210 g/cm ³ |
| Refractive index | 1.4220~1.4320 |

Package: 180Kg Drum

Application:

- It can be used as an additive in cold-curing phenolic and furan foundry resins to improve the flexural strength of sand/resin elements with very long shelf life of the resins.
- It can also be used as glass and metal primers.
- can also be used as additive to phenolic resin binders and mineral-filled composites.

Storage: Stored in cool and dry place, avoid moisture and sunshine.



Recommend Shelf Life: 12 months