

YAC-LY008

SILICONE RESIN

CAS No. --

Specifications:

Tests	Specification
Appearance	White powder
Kinematic viscosity (50% toluene solution)	4.3mm ² /s
Mean particle size	≈100 μ m
HCL (50% toluene solution)	≤10ppm
OH (50% toluene solution)	0.00 - 0.30 %
Apparent density of settlement	0.20 - 0.50 g/cm ³

Package: 20Kg Drum,200Kg Drum.

Application:

- As a basic material, it can be used in defoamer and foam stabilizer, as well as in addition to pressure sensitive adhesive and transparent reinforcement filler.
- In the field of high temperature defoamer, it can effectively improve the high temperature resistance, defoamer and defoamer. In order to meet the defoamer in high temperature system and ink system better performance. Specially, low molecular treatment is carried out to ensure the stability of the product after emulsification.
- In the pressure sensitive adhesive industry, it is to improve the cohesion strength of silicone pressure sensitive adhesive and adjust the peeling force.

Storage: Keep under the condition of 5°C to 30°C in the original sealed container.

Recommend Shelf Life: 12 months.