

YAC-MP1153

SILICONE RESIN

CAS No. --

Specifications:

Tests	Specification
Appearance	Light yellow to reddish brown uniform liquid, Opalescent light is allowed, inorganic mechanical Impurity
Viscosity $(25\pm1^{\circ}C)$	25-55s
Solid content	≥50%
Drying time $(200\pm2^{\circ}\text{C})$	≤1h
Heat resistance $(200\pm2^{\circ})$	≥300h
Thermal weight loss $(200\pm2^{\circ}\mathbb{C})$, 3h	≤5%

Package: 20Kg Drum, 200Kg Drum.

Application:

 It can manufacture soft mica board, soft mica tape, soft glass cloth, glass wire sleeve, glass wire electric tape, moisture-proof high container impregnation paint, and processing paper, etc.

Storage: Keep stored in a cool, dry and ventilated warehouse, prevent direct sunlight, prevent acid, alkali gas and liquid fumigation, isolate fire sources, away from heat sources.

Recommend Shelf Life: 6 months.