


LANSTAB-CAA 30 μ m

Calcium Acetyl Acetonate

CAS No. 19372-44-2

Specifications:



Tests	Specification
Appearance	White crystallion powder
Assay	≥98.0%
Calcium content	16.60~17.50%
Melting point	278.0~282.0°C
Loss on drying (120°C)	≤1.00%
Bulk density	0.20~0.40g/cm ³
Granularity ≤30 μ m	99.5%

Package: 25Kg/Bag

Application:

- It is most commonly used as thermal energy Stabilizer in polyvinyl chloride (PVC). formulation, can also be used as a heat stabilizer for other halogenated polymers. It is also used as a catalyst, resin crosslinker, resin Hardening accelerators, rubber additives, etc.

Storage: Store in cool & dry place, avoid moisture and sunshine.



Recommend Shelf Life: 12 months.